

Test Report No.: 68.431.22.5049.01A

Dated: 2023-02-17



Applicant : The Dreamfarm Pty Ltd
7 Amy St, Albion, QLD 4010, Australia

Sample Description : Fluicer

End use : Juicer

Style No. : DFFU3444, DFFU3451, DFFU3468

Supplier / Manufacturer : Wellbase Industrial Ltd

Buyer : The Dreamfarm Pty Ltd

Country of Origin : China

Country of Destination : Australia, USA, Europe, Japan

Test Sample Receipt Date, Location : 2022-11-28, Shenzhen

Test Period, Location : From 2022-12-12 to 2023-02-17, Shenzhen

Test Result(s) : Refer to Section 3

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : <http://www.tuv sud.cn>

Lab 1 - Chemical testing and
part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Erlu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical
testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



Purpose Of Examination / Conclusion:

No.	Test Item(s)	Conclusion
	As specified by client, to test per the selected requirement(s) for the tested item(s) as stated in the German Food & Feed Acts LFGB (§ 30 & 31) and Regulation (EC) No.1935/2004	
1.	Overall Migration	Pass
2.	Specific Migration of PAA	Pass
3.	Specific Migration of PAAs	Pass
4.	Specific Migration of Heavy Metals	Pass
5.	Total Chromium, Vanadium, Zirconium and Hafnium Content	Pass
6.	Peroxide Value	Pass
7.	Sensory Test Test for compliance with German Food and Feed Acts LFGB Section 31 and Regulation (EC) No. 1935/2004 Article 3(1)	Pass
8.	FDA CFR Title 21 Part 177.1520 (Excluding Density) Test for compliance with the selected requirement(s) in U.S. F.D.A. C.F.R. 21. Part 177.1520	Pass

Remarks:

- (1) The results relate only to the items tested.
- (2) Samples are tested as received.
- (3) The test items and samples were specified by the client
- (4) "Pass" means the measured result is within a limit, even when extended by expanded uncertainty. "Fail" means the measured result is beyond a limit, even when extended by expanded uncertainty. "Inconclusive" means the measured result can be within or beyond a limit when extended by expanded uncertainty. The confidence level of the expended uncertainty for "Pass", "Fail" and "Inconclusive" is 95%.

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuv sud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

Test Report No.: 68.431.22.5049.01A

Dated: 2023-02-17



TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
TÜV SÜD Group

Prepared by:


Reviewed by:



Huang, Jessica
Senior Project Coordinator

Shu, Steven
Senior Project Coordinator

Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production. For further details, please see testing and certification regulation, chapter A-3.4.



Regd. Office:


TüV SüD Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
Fax: +86 755 8828 5299
E-mail: info@tuvsud.com
Web : <http://www.tuvsud.cn>

Lab 1 - Chemical testing and
part of electrical testing
Lab 2 - Physical & mechanical
testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District, Shenzhen, Guangdong, China
Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

1. Photo of the Submitted Sample:



Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District,
Shenzhen, Guangdong, China

Phone: +86 755 8828 6998

Fax: +86 755 8828 5299

E-mail: info@tuv sud.com

Web : http://www.tuv sud.cn


Lab 1 - Chemical testing and
part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical
testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China

2. List of Materials as identified by the Laboratory:

T. No.	Sample No.	Colour and Description	Photograph
T1	001	Yellow plastic	



Regd. Office:

TüV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuv sud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing
 Lab 2 - Physical & mechanical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District, Shenzhen, Guangdong, China
 Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



3. Test Result

3.1 Overall Migration

Test method: With reference to EN 1186-3:2022.

Sample 001 migration ratio(S/V): 10dm²/L

Simulant (s) Used	Test Condition	Result(s) [mg/dm ²]			Maximum Permissible Limit [mg/dm ²]
		001			
		1 st migration	2 nd migration	3 rd migration	
3% Acetic acid	40°C for 0.5 hour	<3.00	<3.00	<3.00	10
20% Ethanol	40°C for 0.5 hour	<3.00	<3.00	<3.00	10

Stability: Comply

3.2 Specific Migration of PAA

Test method: With reference to EN13130-1:2004, followed by Kunststoffe im Lebensmittelverkehr, Book 2, Teil B II,XXI

Test condition: 3% Acetic acid, 40°C for 0.5 hour

Sample 001 migration ratio(S/V): 6dm²/L

Test Item(s)	Result(s) [mg/kg]			Maximum Permissible Limit [mg/kg]
	001			
	1 st migration	2 nd migration	3 rd migration	
Total Primary Aromatic Amine	<0.01	<0.01	<0.01	0.01

Stability: Comply

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuv sud.com
 Web : http://www.tuv sud.cn

Lab 1 - Chemical testing and part of electrical testing
 Lab 2 - Physical & mechanical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District, Shenzhen, Guangdong, China
 Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



3.3 Specific Migration of PAAs

Test method: With reference to EN 13130-1:2004, followed by LC/MS/MS

Test condition: 3% Acetic acid, 40°C for 0.5 hour

Sample 001 migration ratio(S/V): 6dm²/L

Test Item(s)	CAS No.	Result(s) [mg/kg]			Maximum Permissible Limit[mg/kg]
		001			
		1 st migration	2 nd migration	3 rd migration	
4-aminobiphenyl	92-67-1	ND	ND	ND	ND(DL:0.002)
benzidine	92-87-5	ND	ND	ND	ND(DL:0.002)
4-chloro-o-toluidine	95-69-2	ND	ND	ND	ND(DL:0.002)
2-naphthylamine	91-59-8	ND	ND	ND	ND(DL:0.002)
o-aminoazotoluene	97-56-3	ND	ND	ND	ND(DL:0.002)
5-nitro-o-toluidine	99-55-8	ND	ND	ND	ND(DL:0.002)
4-chloroaniline	106-47-8	ND	ND	ND	ND(DL:0.002)
4-methoxy-m-phenylenediamine	615-05-4	ND	ND	ND	ND(DL:0.002)
4,4'-diaminodiphenylmethane	101-77-9	ND	ND	ND	ND(DL:0.002)
3,3'-dichlorobenzidine	91-94-1	ND	ND	ND	ND(DL:0.002)
3,3'-dimethoxybenzidine	119-90-4	ND	ND	ND	ND(DL:0.002)
3,3'-dimethylbenzidine	119-93-7	ND	ND	ND	ND(DL:0.002)
4,4'-methylenedi-o-toluidine	838-88-0	ND	ND	ND	ND(DL:0.002)
p-cresidine	120-71-8	ND	ND	ND	ND(DL:0.002)
4,4'-methylene-bis-(2-chloro-aniline)	101-14-4	ND	ND	ND	ND(DL:0.002)
4,4'-oxydianiline	101-80-4	ND	ND	ND	ND(DL:0.002)
4,4'-thiodianiline	139-65-1	ND	ND	ND	ND(DL:0.002)
o-toluidine	95-53-4	ND	ND	ND	ND(DL:0.002)
4-methyl-m-phenylenediamine	95-80-7	ND	ND	ND	ND(DL:0.002)
2,4,5-trimethylaniline	137-17-7	ND	ND	ND	ND(DL:0.002)
o-anisidine	60-09-3	ND	ND	ND	ND(DL:0.002)
4-amino azobenzene	90-04-0	ND	ND	ND	ND(DL:0.002)
1,3-phenylenediamine	108-45-2	ND	ND	ND	ND(DL:0.002)
2,4-Dimethylaniline	95-68-1	ND	ND	ND	ND(DL:0.002)*
2,6-dimethyl-aniline	87-62-7	ND	ND	ND	ND(DL:0.002)*
Aniline	62-53-3	ND	ND	ND	ND(DL:0.002)*
p-Phenylenediamine	106-50-3	ND	ND	ND	ND(DL:0.002)*
1,5-Naphthalenediamine	2243-62-1	ND	ND	ND	ND(DL:0.002)*
2,6-toluenediamine	823-40-5	ND	ND	ND	ND(DL:0.002)*
Stability: Comply					

- Note 1. ND denotes Not Detected and less than Detection Limit (Detection Limit=0.002mg/kg).
 2. * denotes Limit specified by client

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuv sud.com
 Web : http://www.tuv sud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



3.4 Specific Migration of Heavy Metals

Test method: With reference to EN13130-1:2004, followed by ICP-MS.

Test condition: 3% Acetic acid, 40°C for 0.5 hour

Sample 001 migration ratio(S/V): 6dm²/L

Test Item(s)	Result(s) [mg/kg]			Maximum Permissible Limit [mg/kg]
	001			
	1 st migration	2 nd migration	3 rd migration	
Lithium (Li)	<0.1	<0.1	<0.1	0.6
Aluminium (Al)	<0.1	<0.1	<0.1	1
Chromium (Cr)	ND	ND	ND	ND (DL:0.01)
Manganese (Mn)	<0.1	<0.1	<0.1	0.6
Iron (Fe)	<5	<5	<5	48
Cobalt (Co)	<0.01	<0.01	<0.01	0.05
Nickel (Ni)	<0.01	<0.01	<0.01	0.02
Copper (Cu)	<1	<1	<1	5
Zinc (Zn)	<1	<1	<1	5
Arsenic (As)	ND	ND	ND	ND (DL:0.01)
Cadmium (Cd)	ND	ND	ND	ND (DL:0.002)
Antimony (Sb)	<0.01	<0.01	<0.01	0.04
Barium (Ba)	<0.1	<0.1	<0.1	1
Mercury (Hg)	ND	ND	ND	ND (DL:0.01)
Lead (Pb)	ND	ND	ND	ND (DL:0.01)
Lanthanum (La)	<0.01	<0.01	<0.01	0.05
Europium (Eu)	<0.01	<0.01	<0.01	0.05
Gadolinium (Gd)	<0.01	<0.01	<0.01	0.05
Terbium (Tb)	<0.01	<0.01	<0.01	0.05
Sum of [La, Eu, Gd, Tb]	<0.04	<0.04	<0.04	0.05
Stability: Comply				

- Note
1. DL denotes Detection Limit
 2. ND denotes Not Detected and less than Detection Limit.

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuv sud.cn
 Web : http://www.tuv sud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



3.5 Total Chromium, Vanadium, Zirconium and Hafnium Content

Test method: Microwave digestion, followed by AAS or ICP-OES analysis

Test Item(s)	Result(s)[mg/kg]	Maximum Permissible Limit [mg/kg]
	001	
Chromium content	<2.0	10
Vanadium content	<15.0	20
Zirconium content	<15.0	100
Hafnium Content	<15.0	100

3.6 Peroxide Value

Test method: With reference to Bundesgesundheitsbl. 40 (1997), 412.

Test Item(s)	Result(s)	Maximum Permissible Limit
	001	
Peroxide Value	Absent	Absent

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuv sud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and
 part of electrical testing
 Lab 2 - Physical & mechanical
 testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District, Shenzhen, Guangdong, China
 Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China



3.7 Sensory test

Test method: With reference to DIN 10955:2004

The submitted sample was simulated in distilled water at 40°C for 0.5 hour. After this treatment treated water was examined by panels with regard to any divergence in smell and taste.

Sample(s)	Testing Parameter	Grading result(s)	Recommended level
001	Transfer of taste	0	<3
	Transfer of smell	0	<3

Note: 1. Available grading are listed as follow:

Grading 0: No perceptible taste/smell deviation

1: Just perceptible taste/smell deviation

2: Weak taste/smell deviation

3: Clear taste/smell deviation

4: Strong taste/smell deviation

3.8 FDA 21 CFR Part 177.1520 (Excluding Density)

Test for compliance with the selected requirement(s) in U.S. F.D.A. C.F.R. 21. Part 177.1520

Test Item(s)	Result(s)	FDA Specification
	001	
Melting Point (°C)*	164.8	160-180
n-Hexane extractives at reflux temperature, w/w (%)	0.97	6.4
Xylene extractives (%) at 25°C, w/w (%)	1.66	9.8

Note: Specification is quoted from US FDA 21 CFR Part 177.1520 (C) 1.1a Polypropylene.

-- END OF TEST REPORT--

Regd. Office:

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
 Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District,
 Shenzhen, Guangdong, China

Phone: +86 755 8828 6998
 Fax: +86 755 8828 5299
 E-mail: info@tuvsud.com
 Web : http://www.tuvsud.cn

Lab 1 - Chemical testing and part of electrical testing

Building 12&13, Zhiheng Wisdomland Business Park, Guankou Ertu, Nantou, Nanshan District, Shenzhen, Guangdong, China

Lab 2 - Physical & mechanical testing

Building A2, Jin'ao Industrial Park, No. 150, Jingfang Road, Fuhai, Baoan District, Shenzhen, Guangdong, China